



Science.
Applied to Life.™

Prestige

Let in the light. Not the heat. Superior comfort and clarity with 3M™ Sun Control Window Film Prestige Series.

- ▶ High visible light transmission providing excellent aesthetics
- ▶ Up to 97% infrared rejection providing energy savings and enhanced comfort*
- ▶ Low interior and exterior reflectivity enhances views while maintaining exterior appearance
- ▶ Non-metalized film with no signal interference and no chance for corrosion
- ▶ Helps extend the life of furnishings by significantly reducing harmful UV rays, the largest cause of fading
- ▶ The Prestige Series can become carbon negative in as short as 6 months from install**
- ▶ Comprehensive warranty from 3M

Visible Light Transmission ★★★★★

Low Reflection ★★★★★

Infrared Rejection ★★★★★

Best ★★★★★

Better ★★★★

Good ★★★

Fair ★★

Not Recommended ★

In comparison to other 3M™ Sun Control Window Films

**IR Rejection as measured from 900–1000nm*

***Based on emission calculations performed in compliance with the GHG Protocol Product Life Cycle Accounting and Reporting Standard (2011), third party assured by Quality Associates incorporated and energy savings calculation completed by CONSOL Energy. Contact 3M for details.*

Beauty and performance that metallic films can't match.



Valued
Associations
and Alliances:



CLINTON
CLIMATE
INITIATIVE



Climate Zone 3

Caribe Resort, Orange Beach, Alabama





Approximately 600 sq ft of windows installed with Prestige 40

Customer Issues:

- ▶ Protecting furnishings from damaging effects of the sun
- ▶ With no change to the exterior appearance of the 14-story building



Product Performance and Technical Data

Glass Type (All 1/4")	Film Type	Visible Light			Total Solar Energy Rejected		Solar Heat Gain Coefficient (G Value)	U Value		Solar Heat Reduction	UV Light Rejected	Glare Reduction	Visible Light to Solar Heat Gain Ratio
		Reflected (Interior)	Reflected (Exterior)	Transmitted	Normal	60 Degree Angle		btu/hft²F	w/m²K				
 Clear	PR40	7%	7%	39%	60%	66%	0.40	0.99	5.6	50%	99.9%	55%	1.0
	PR50	7%	8%	50%	56%	63%	0.44	0.99	5.6	46%	99.9%	44%	1.1
	PR60	8%	8%	60%	53%	61%	0.47	0.99	5.6	42%	99.9%	32%	1.3
	PR70	9%	9%	69%	50%	59%	0.50	0.99	5.6	38%	99.9%	22%	1.4
 Tinted	PR40	6%	5%	24%	63%	67%	0.37	0.99	5.6	41%	99.9%	55%	0.6
	PR50	6%	6%	30%	61%	66%	0.39	0.99	5.6	38%	99.9%	43%	0.8
	PR60	7%	6%	36%	59%	63%	0.41	0.99	5.6	34%	99.9%	32%	0.9
	PR70	7%	6%	42%	57%	63%	0.43	0.99	5.6	31%	99.9%	22%	1.0
 Double Clear	PR40	8%	14%	35%	49%	54%	0.51	0.47	2.7	27%	99.9%	55%	0.7
	PR50	9%	15%	45%	47%	53%	0.53	0.47	2.7	25%	99.9%	44%	0.8
	PR60	11%	15%	54%	46%	54%	0.54	0.47	2.7	22%	99.9%	32%	1.0
	PR70	13%	15%	62%	44%	50%	0.56	0.47	2.7	21%	99.9%	22%	1.1
 Double Tinted	PR40	8%	8%	21%	61%	64%	0.39	0.47	2.7	23%	99.9%	55%	0.5
	PR50	9%	8%	27%	60%	64%	0.40	0.47	2.7	22%	99.9%	44%	0.7
	PR60	10%	8%	32%	59%	64%	0.41	0.47	2.7	20%	99.9%	32%	0.8
	PR70	12%	8%	37%	59%	62%	0.42	0.47	2.7	18%	99.9%	22%	0.9

LEED Certification

Window films may be used toward the following LEED credits

▶ SS-8 ▶ MR 1.1-1.2 ▶ EQ-7.1 ▶ EQ-8.1-8.2 ▶ EA-1 ▶ MR 5.1-5.2 ▶ EQ-7.2 ▶ ID

Warranty and Limited Remedy: 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER EXPRESS OR IMPLIED WARRANTIES OR CONDITIONS, INCLUDING ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. If the 3M product does not conform to this warranty, the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price. **Limitation of Liability:** Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted.



Renewable Energy Division
3M Center, Building 235-2S-27
St. Paul, MN 55144-1000
3M.com/windowfilm

3M is a trademark of 3M.
Used under license in Canada.

Please recycle. Printed in the U.S.A.
© 3M 2016. All rights reserved.
98-0150-0756-4